

EXT. REFLECTIVE SILVER 55

External Reflective Silver 55 is highly effective at reducing solar heat gain, whilst at the same time continuing to allow most natural light to pass through. A light privacy film, it does not fully prevent vision from both sides of the glass pane.



Tintfit Window Films warranty

VERTICAL 4 YEARS
HORIZONTAL N/A



Fire-resistance rating

M1



Storage from -5°C to +40°C

3 YEARS



REACH RoHS compliant

RESPECTED

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	52 %
Reflection of external visible light	26 %
Reflection of internal visible light	26 %
Total solar energy rejected	56 %
Total solar energy rejected 2	60 %
Solar ratio :	
Solar energy reflection	30 %
Solar energy absorption	33 %
Solar energy transmission	37 %
Reduction in Solar Glare	44 %
g-value	0.44
u-value	5.5
Shading coefficient	0.4


Installation type : External application

Roll length	30,5 m
PET / PVC composition	PET
Thickness	50 µ

Colour : SILVER LIGHT

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester, with anti IR metal particles deposit
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution, do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data, Tintfit Window Films reserves the right to modify the composition of its films at any time.

INSTALLATION ADVICE

Vertical installation and on standard glass surface*

Clear single pane	✓
Tinted single pane	✓
Reflective tinted single pane	✓
Clear double pane	✓
Tinted double pane	✓
Reflective tinted double pane	✓
Gas-filled double pane - Low E	✓
STADIP EXT. clear double pane	✓
STADIP INT. clear double pane	✓

✓ Yes ! Caution ✗ No

*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.